

U.S. Corporate Headquarters 400 Vallev Rd. Warrington, PA 18976 1(800) 523-2575 / (215) 343-6484 1(800)343-3291 fax info@polvsciences.com

Polysciences Europe GmbH Badener Str 13 69493 Hirschberg an der Bergstrasse, Germany . +(49) 06201-845200 +(49) 06201-8452020 fax info@polysciences.de

Polysciences Asia-Pacific, Inc. 2F-1, 207 DunHua N. Rd. Taipei, Taiwan 10595 (886) 2 8712 0600 (886) 2 8712 2677 fax info@polvsciences.tw


TECHNICAL DATA SHEET 1001

Page 1 of 1

Polybead[®] Poly(methyl methacrylate) Microspheres Catalog Numbers: 12083, 19130, 23570, 26305

DESCRIPTION

The Polybead® Poly(methyl methacrylate) or PMMA Microspheres are solid, non-porous spheres. PMMA is less hydrophobic than polystyrene and should show reduced nonspecific protein and peptide binding. The density of PMMA (i.e. ~1.19 g/cm³) is considerably higher than that of polystyrene beads, which makes them easier to concentrate via centrifugation. PMMA bead suspensions do contain surfactant as well as surface carboxyl groups at higher densities than the standard Polybead® Carboxylate polystyrene microspheres.



Polybead PMMA Microspheres – Broad Distribution (Cat. #19130)

Polybead® PMMA Microspheres with Anionic Surfactant (Cat. #23570).

(Gal. #23370).	
Diameter range:	0.
Concentration:	~5
Density:	~1
Surface functional groups:	Са

08 – 0.09µm 5% solids 1.19 g/cm³ arboxylate, methyl ester

STORAGE

Store suspensions at 4°C. Do not permit to freeze. Dry microspheres may be stored at room temperature.

These products are for research use only and are not intended for use in humans or for in vitro diagnostic use.

CHARACTERISTICS

Polybead[®] PMMA Microspheres – Monodisperse

(Cat. #12083): Diameter:

Density:

0.30µm Concentration: ~2.5% solids ~1.19 g/cm³ Surface functional groups: Carboxylate, methyl ester

Polybead® PMMA Microspheres – Broad Distribution (Cat. #19130, 26305):

Diameter range:	1-10µm
Concentration:	~5% solids, or 100% (dry)
Density:	~1.19 g/cm ³
Surface functional groups:	Carboxylate, methyl ester

ORDERING INFORMATION

Cat. #	Description	Sizes
12083	Polybead® PMMA Microspheres - Monodisperse, 0.30µm	10ml
19130	Polybead [®] PMMA Microspheres - Broad Distribution	10ml
26305	Polybead [®] PMMA Microspheres - Broad Distribution (Dry)	500mg
23570	Polybead [®] PMMA Microspheres with Anionic Surfactant	10ml

TO ORDER

In The U.S. Call:	1(800) 523-2575 • (215) 343-6484
In The U.S. Fax:	1(800) 343-3291 • (215) 343-0214
In Germany Call:	+(49) 06201-845200
In Germany Fax:	+(49) 06201-8452020
In Asia Call:	(886) 2 8712 0600
In Asia Fax:	(886) 2 8712 2677

Order online anytime at www.polysciences.com

Should any of our materials fail to perform to our specifications, we will be pleased to provide replacements or return the purchase price. We solicit your inquiries concerning all needs for life sciences work. The information given in this bulletin is to the best of our knowledge accurate, but no warranty is expressed or implied. It is the user's responsibility to determine the suitability for their own use of the products described herein, and since conditions of use are beyond our control, we disclaim all liability with respect to the use of any material supplied by us. Nothing contained herein shall be construed as a recommendation to use any product or to practice any process in violation of any law or any government regulation