



Corporate Headquarters
400 Valley Road
Warrington, PA 18976
1-800-523-2575
FAX 1-800-343-3291
Email: info@polysciences.com
www.polysciences.com

Europe - Germany
Polysciences Europe GmbH
Handelsstr. 3
D-69214 Eppelheim, Germany
(49) 6221-765767
FAX (49) 6221-764620
Email: info@polysciences.de

Low Viscosity Glob Top Encapsulant PC8007

PC8007 is a high performance epoxy for encapsulation applications. The product is well suited for many bonding and sealing uses requiring high modulus and high temperature resistance.

Product Features:

- High Thermal Resistance
- Rigid and High Strength
- Durable
- Low Viscosity

PC8007 (typical properties, values approximate)

Composition	Epoxy
Appearance	Black liquid
Viscosity @25C,	4,000cps
Specific Gravity	1.72

Optimum Cure Cycle 60 minutes @ 100°C + 60 minutes @ 165°C

Cured Properties (typical properties)

Tg	160°C
CTE	< 20 ppm

Usage:

PC8007 is stored frozen to extend its shelf life, the product must be thawed prior to use. Apply the thawed product to the bonding surface and cure at the recommended curing cycle.

Shelf Life : 12 months frozen.

Ordering Information

In The U.S. Call: 1-800-523-2575 • 215-343-6484
In The U.S. Fax: 1-800-343-3291 • 215-343-0214

In Europe Call: (49) 6221-756767
In Europe Fax: (49) 6221-764620

Should any of our materials fail to perform to our specifications, we will be pleased to provide replacements or return the purchase price. We solicit your inquiries concerning all needs for life sciences work. The information given in this bulletin is to the best of our knowledge accurate, but no warranty is expressed or implied. It is the user's responsibility to determine the suitability for his own use of the products described herein, and since conditions of use are beyond our control, we disclaim all liability with respect to the use of any material supplied by us. Nothing contained herein shall be construed as a recommendation to use any product or to practice any process in violation of any law or any government regulation.